

## AUXILIARY REQUEST

We Claim:

1. A first oriented film comprising a first polyethylene composition which comprises:  
from 20 to 50 wt% of a first linear low density polyethylene polymer having a density greater than 0.925 g/cc and an  $I_2$  lower than 2 g/10min; and  
from 80 to 50 wt% of a second linear low density polyethylene polymer having a density lower than or equal to 0.925 g/cc and an  $I_2$  greater than 2 g/10min;  
wherein the first polyethylene composition has an  $I_2$  from 0.5 to 10 g/10min and a density from 0.910 to 0.940 g/cc  
wherein the first oriented film is produced by a tenter frame process.
2. The first oriented film according to claim 1, wherein the first and/or second linear low density polyethylene polymer is produced using a Ziegler-Natta catalyst.
3. The first oriented film according to claim 1, wherein the first linear low density polyethylene polymer has a density greater than 0.930 g/cc and an  $I_2$  lower than 1 g/10min.
4. The first oriented film according to claim 1, wherein the second linear low density polyethylene polymer has a density lower than 0.920 g/cc and an  $I_2$  greater than 4 g/10min.
5. The first oriented film according to claim 1, wherein the first polyethylene composition has an  $MW_{HDF>95}$  greater than 135 kg/mol and  $I_{HDF>95}$  greater than 42 kg/mol.